


Palladium® G2 Rubrails

Suggested Specification



- Manufactured with G2 BioBlend™, Inpro's exclusive blend of PETG and biopolymer.
- Perfect for trouble spots that endure commercial damage
- Achieve a professional, finished look with factory beveled top and bottom edges
- Offer the same variety of protection levels as Palladium® G2 Sheet
- Meets the most rigorous standards and criteria of chemical emissions as prescribed by the GREENGUARD Environmental Institute
- Has been tested and meets GREENGUARD Environmental Institute's and the state of California's requirements for low emitting products as tested by Air Quality Sciences
- Has been tested and meets the GREENGUARD Children & School chemical emissions levels



IPC.1126/REV.10

Palladium® G2 Rubrails

Suggested Specifications

PART 1 - GENERAL

1.01 SUMMARY

A. Non PVC rubrails for wall protection and decoration

1.02 SECTION INCLUDES

A. Palladium® G2 Rubrails

1.03 REFERENCES

- A. American Society for Testing and Materials (ASTM)
- B. National Fire Protection Association (NFPA)
- C. Society of Automotive Engineers (SAE)

1.04 SYSTEM DESCRIPTION

A. Performance Requirements: Provide Palladium® G2 Rubrails that conforms to the following requirements of regulatory agencies and the quality control of IPC Door and Wall Protection Systems™, InPro Corporation.

1. Fire Performance Characteristics: Provide material conforming with the NFPA Class A fire rating. Surface burning characteristics, as determined by ASTM E-84, shall be flame spread of 25 or less and smoke development of 450 or less.
 2. Impact Strength: Provide materials that have been tested in accordance with the applicable provisions of ASTM D-256, Impact Resistance of Plastics.
 3. Chemical and Stain Resistance: Provide material that shows resistance to stain when tested in accordance with applicable provisions of ASTM D-543.
 4. Fungal and Bacterial Resistance: Provide material that does not support fungal or bacterial growth as tested in accordance with ASTM G-21 and ASTM G-22.
 5. GREENGUARD Certified: Provide GREENGUARD Certified sheet. Sheet shall meet the requirements of GREENGUARD Certification Standards for Low-Emitting Products and GREENGUARD Product Emission Standard for Children & Schools.
 6. Color Consistency: Provide components matched in accordance with SAE J-1545 - (Delta E) with a color difference no greater than 1.0 units using CIE Lab, CIE CMC, CIE LCh, Hunter Lab or similar color space scale systems.
- 1.05 SUBMITTALS
- A. Product Data: Manufacturer's printed product data for each type of G2 Series Rubrails specified.
 - B. Detail Drawings: Mounting details with the appropriate adhesives for specific project substrates.
 - C. Samples: Verification samples of Palladium® G2 Rubrails, 8" (203mm) square, of each type and color indicated.
 - D. Manufacturer's Installation Instruction: Printed installation instructions for Palladium® G2 Rubrails.

1.06 DELIVERY, STORAGE AND HANDLING

- A. Deliver materials in unopened factory packaging to the jobsite
- B. Inspect materials at delivery to assure that specified products have been received.

C. Store in original packaging in a climate controlled location away from direct sunlight.

1.07 PROJECT CONDITIONS

A. Environmental Requirements: Products must be installed in an interior climate controlled environment.

1.08 WARRANTY

A. Standard InPro Limited Lifetime Warranty against material and manufacturing defects.

PART 2 - PRODUCTS

2.01 MANUFACTURER

- A. Acceptable Manufacturer: IPC Door and Wall Protection Systems™, InPro Corporation, PO Box 406, Muskego, WI 53150, USA; Telephone: 800.222.5556, Fax: 888.715.8407, www.inprocorp.com
- B. Substitutions: Not permitted
- C. Provide all Palladium® G2 Rubrails and wall protection from a single source.

2.02 MANUFACTURED UNITS

- A. Palladium® G2 Rubrails
 1. Thickness: G2-R4 .040" = 3/64" (1mm)-standard
G2-R6 .060" = 1/16" (1.5mm)-standard
- Backing: Unbacked
- Height: Maximum 24" (610mm)
- Length: 8' (2.44m)
- B. Adhesives
 1. 3M Fastbond Contact Cement, a water dispersed contact cement
 2. InPro Bond Adhesive, a freeze-thaw stable trowelable adhesive
 3. XT-2000+ Adhesive, a freeze-thaw stable trowelable adhesive.

2.03 MATERIALS

- A. BioPolyPETG+™ sheet material shall be extruded from chemical and stain-resistant reformulated PETG.

2.04 ACCESSORIES

- A. Top caps, vertical divider bars and inside corners: Accessory trim pieces shall be extruded from chemical and stain resistant non-PVC thermoplastic.
- B. Color Matched Caulk

2.05 FINISHES

- A. Color or pattern of Palladium® G2 Rubrails to be selected by the architect from the InPro finish selection. Surface shall have a velvet texture.
- B. Accessories: Color Matched Caulk shall be of a color matching the Palladium® G2 Rubrails
- C. Top caps, vertical divider bars and inside corner colors to be selected by the architect from the InPro finish selection. Surface shall have a smooth finish.

PART 3 - EXECUTION

3.01 EXAMINATION

A. Examine areas and conditions in which the Non PVC sheet will be installed.

1. Complete all finishing operations, including painting, before beginning installation of sheet materials.
- B. Wall surface shall be dry and free from dirt, grease and loose paint.

3.02 PREPARATION

A. General: Prior to installation, clean substrate to remove dust, debris and loose particles. Paint substrate with a paint or primer that does not contain Polyvinyl Acetate (PVA).

3.03 INSTALLATION

- A. General: Locate the sheet as indicated on the approved detail drawing for the appropriate substrate and in compliance with the InPro installation instructions. Install level and plumb at the height indicated on the drawings.
- B. Installation of Palladium® G2 Rubrails
 1. Adhere to substrate with InPro Bond, a freeze-thaw stable, nonflammable, high strength, water based adhesive that trowels on and allows approximately 20 minutes working time before firming.
 2. Adhere to substrate with Fastbond 30, a nonflammable, high strength, water dispersed contact adhesive, with very little odor. Smooth roll surface.

3.04 CLEANING

A. At completion of the installation, clean surfaces in accordance the InPro cleanup and maintenance instructions.